




INVESTOR IN PEOPLE



The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

IB/04/52105

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

**CERTIFIED COPY OF
PRIORITY DOCUMENT**

Signed

Evans.

Dated 3 August 2004

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

The
Patent
Office

THE PATENT OFFICE

22 OCT 2003

NEWPORT

22OCT03 EB46274-1 DO 879
P01/7700 0.00-0324561.0

1/77

Request for grant of a patent
(See notes on the back of this form. You can
also get an explanatory leaflet from the Patent
Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
Gwent NP10 8QQ

- | | | | |
|--|--|---------------------------------|----------------|
| 1. Your reference | PHGB030192GBP | | |
| 2. Patent application number
(The Patent Office will fill in this part) | <div style="text-align: right;">22 OCT 2003</div> <div style="text-align: center; font-size: 1.2em;">0324561.0</div> | | |
| 3. Full name, address and postcode of the or of each applicant (<u>underline all surnames</u>) | KONINKLIJKE PHILIPS ELECTRONICS N.V.
GROENEWOUDSEWEG 1
5621 BA EINDHOVEN
THE NETHERLANDS
07419294001 ✓ | | |
| Patents ADP Number (if you know it) | | | |
| If the applicant is a corporate body, give the country/state of its incorporation | THE NETHERLANDS | | |
| 4. Title of the invention | A METHOD OF PRODUCING A CONDUCTIVE LAYER ON A SUBSTRATE | | |
| 5. Name of your agent (if you have one) | | | |
| "Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode) | Philips Intellectual Property & Standards
Cross Oak Lane
Redhill
Surrey RH1 5HA | | |
| Patents ADP number (if you know it) | 08359655001 ✓ | | |
| 6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number | Country | Priority Application number | Date of filing |
| 7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application | Number of earlier application | Date of filing (day/month/year) | |
| 8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer "Yes" if: | YES | | |
| a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or
c) any named applicant is a corporate body.
See note (d)) | | | |

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form.
Do not count copies of the same document.

Continuation sheets of this form

Description	7
Claims(s)	3
Abstract	1
Drawings	8

10. If you are also filing any of the following, state how many against each item:

Priority Documents

Translations of priority documents
Statement of inventorship and right
to grant of a patent (*Patents Form 7/77*)
Request for preliminary examination and
search (*Patents Form 9/77*)
Request for substantive examination
(*Patents Form 10/77*)
Any other documents
(*Please specify*)

11. I/We request the grant of a patent on the basis of this application.

Signature

D. J. Sharrock

Date 21 OCT 03.

12. Name and daytime telephone number of person to contact in the United Kingdom

01293 815399

D. J. SHARROCK

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- If you have answered "Yes" Patents Form 7/77 will need to be filed.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

DESCRIPTION

A METHOD OF PRODUCING A CONDUCTIVE LAYER ON A SUBSTRATE

5 This application relates to a method of producing a conductive layer on a substrate and a device made using the method, particularly but not exclusively to using a photodefinable damascene process for producing conductive layers on substrates, for example for use as address lines in Active Matrix Liquid Crystal Displays (AMLCDs).

10

As LCD matrix arrays get larger and more complex, the requirement to obtain low resistance address lines becomes progressively more important. One way to reduce line resistance is to produce thicker address lines using, for example, a damascene process.

15

WO-A-02/47447 discloses a method of forming a printed circuit board using an ink jet printhead, by printing a three dimensional groove using a curable, non-conductive deposition liquid and depositing a liquid in the groove that dries to form a conductive track. In this case, the groove is defined by the walls printed on either side of it. However, the ink jet method is not particularly

20 suitable for obtaining coverage over large areas, as required for an LCD matrix array. Furthermore, the ink jet method will suffer from the disadvantage of having a periodicity due to the droplets needing to overlap along the edge of the groove.

25

The present invention aims to address the above problems. The invention also aims to provide alternative ways of defining grooves for receiving a conductive material.

According to a first aspect of the invention, there is provided a method of producing a conductive layer on a substrate, comprising the steps of

30 defining a groove for the conductive layer using a photodefinable insulator material and filling the groove with a material capable of forming the conductive layer.

The groove defined in the photodefinable insulator material can have steep walls and so may provide for good confinement of the conductive material. It may also tend to result in a groove with rounded top edges, which may assist in preventing fractures developing in subsequent layers which are
5 deposited over the groove and which descend into the groove to connect to the conductive material within it.

The method may advantageously be used for providing conductive layers on substrates to be used in active matrix liquid crystal displays.

According to the invention, there is also provided a device comprising a
10 substrate overlaid with a photodefinable insulator material, the material having a groove for a conductive layer defined therein. The device may further include a conductive layer in the groove.

The device may be an active matrix liquid crystal display.

According to a second aspect of the invention, there is provided a
15 method of producing a conductive layer on a substrate, comprising the steps of defining a groove for the conductive layer and blading a material capable of forming the conductive layer into the groove.

Blading techniques commonly used in the filling of clichés for offset lithography printing processes may advantageously be adapted for use in
20 producing a conductive layer on a substrate according to the second aspect of invention. The method may provide for a very quick way of filling the groove with an even amount of material.

The groove may be defined by printing an insulating layer onto the substrate so as to define the groove or by depositing a material onto the
25 substrate and subsequently defining the groove in the deposited material, which may be a photodefinable insulator.

According to a third aspect of the invention, there is provided a method of producing a conductive layer on a substrate for an active matrix liquid crystal display, the method comprising the steps of printing an insulating
30 material onto the substrate such that the printed material defines a groove for the conductive layer and filling the groove with a material capable of forming the conductive layer.

Printing techniques may be advantageously used in the production of substrates for active matrix liquid crystal displays.

For a better understanding of the invention, embodiments thereof will now be described, purely by way of example, with reference to the accompanying drawings, in which:

Figure 1 is a schematic illustration of an AMLCD incorporating thin film transistors (TFTs);

Figures 2a to 2f illustrate the steps in the production of a conductive layer, for example a row or column address line in Figure 1, according to the invention;

Figure 3 is a flow diagram explaining the processes used for the production of the stages in Figures 2a to 2c of Figure 2;

Figure 4 is a flow diagram illustrating an alternative process for producing a groove on a substrate according to the invention;

Figure 5 is a flow diagram illustrating a further alternative process for producing a groove on a substrate according to the invention;

Figure 6 is a flow diagram illustrating the steps required to fill the groove produced by any method according to the invention, so as to produce a conductive layer in the groove; and

Figure 7 is a plan view of a substrate with a sea of insulating material printed onto it to define a groove.

Referring to Figure 1, an AMLCD panel is formed on an electrically insulating substrate 1 that may be optically transparent, on which an active switching matrix of LCD pixels P is provided, in a manner well known in itself in the art. Reference is directed to our EP-A-0 629 003. The substrate may also be semiconductive e.g. for a liquid crystal on silicon display, or conductive with an insulating layer beneath the TFTs and other conductive elements to prevent shorting. The pixels $P_{x,y}$ are arranged in a rectangular x, y array and are operated by x and y driver circuits, via row and column address lines.

Considering the pixel $P_{0,0}$ by way of example, it includes a liquid crystal display element $L_{0,0}$ which is switched between different optical transmissivities by means of $TFT_{0,0}$ that has its gate connected to driver line x_0 and its source coupled to driver line y_0 . By applying suitable voltages to the lines x_0 , y_0 , transistor $TFT_{0,0}$ can be switched on and off and thereby control the operation of the LCD element $L_{0,0}$. It will be understood that each of the pixels P of the display is of a similar construction and that the pixels can be scanned row by row on operation of the x and y driver circuits in a manner well known in itself.

Referring to Figures 2a to 2f, Figure 2a illustrates a substrate 1, for example a glass substrate, prior to processing. Figure 2b shows the substrate 1 overlaid with a photodefinable insulator material 2. Figure 2c illustrates a groove 3 formed in the insulator material 2, with rounded edges 4 at the top of the groove 3. Figure 2d illustrates the groove 3 filled with a conductive ink 5. Figure 2e illustrates the conductive ink 5 after curing and Figure 2f illustrates the resulting structure after the layer of photodefinable insulator material 2 has been reduced in thickness.

Referring to Figures 2 and 3, the photodefinable insulator material 2, is for example HD Microsystems™ PI-2730 series polyimide material, such as PI-2731 or HD Microsystems™ HD8000 series polyimide material. The steps required to process this and other similar photodefinable materials are well-known to the skilled person and will therefore only be described in outline in this specification. For further details, reference is directed to HD Microsystems™ PI-2730 Series Low Stress Photodefinable Polyimide Product Information and Process Guidelines.

The photodefinable insulator material 2 is deposited onto the substrate in any one of a number of possible ways, including spin coating, printing, spraying or blading (step s1). The material 2 is then partially cured using a bake process (step s2), which leaves the insulator material dry but soluble in developer solution. The required groove pattern is then produced by light exposure of all areas except the groove 3, using the Mercury broadband spectrum, or G-line (step s3). The PI-2730 series material is, for example, negative working so that exposed areas become insoluble. The resulting

material is then developed, for example using HD Microsystems™ DE-9040 developer solution and rinsed with HD Microsystems™ RI-9140 rinse solution or N-Butylacetate (step s4). A final curing step is then carried out (step s5). The material tends to be left with a curved profile, as shown in Figure 2c, which is advantageous in that subsequent layers can pass over the top of the groove and connect to any structure within the groove with a reduced probability of fracture at the smooth edge 4.

There are a number of alternative routes which would be well known to those skilled in the art for defining the groove, depending on the insulator material being used. For example, referring to Figure 4, for either a photodefinable or non-photodefinable insulator material, the material 2 is deposited on the substrate 1 by any suitable technique (step s10), fully cured (step s11) and a metal layer, for example aluminium, is then sputtered onto the insulator to form a hard, in situ, mask (step s12). The metal layer is coated with a photoresist (step s13) and this is pre-baked (step s14). The required groove pattern is then exposed (step s15), developed (step s16) and the photoresist post-baked (step s17). The exposed metal in the groove is wet etched (step s18) to define the groove pattern in the insulator material 2 underneath. The photoresist may then be stripped off (step s19) and the organic insulator 2 underneath the metal layer is then dry etched (step s20) to define the groove 3. Alternatively, rather than stripping the photoresist at step s19, this step may be omitted, in which case the etchants used in step s20 will remove the photoresist. Finally, the metal mask is stripped off to produce the structure shown in Figure 2c (step s21).

In a further example shown in Figure 5, the insulator material 2 is deposited (step s30), partly cured (step s31), coated with a photoresist (step s32) and the photoresist exposed (step s33) to define the groove pattern. The photoresist is then developed (step s34), and development is continued, a process which is also referred to as wet etching, to remove the organic layer 2 to form the groove 3 (step s35). The photoresist is then removed (step s36) and the insulator fully cured (step s37).

Referring to Figure 6, once the groove 3 has been defined, it is filled with a desired metal precursor 5 or suspension of particles in a printing medium, or ink, using a doctor blade, by analogy to the way a printing cliché would be filled with ink (step s40). This leaves the groove 3 filled with the
5 conductive ink 5, as shown, for example, in Figure 2d.

The conductive ink is then cured (step s41) to obtain a highly conducting medium. After curing, a descum planar etching process may be performed to remove any excess material remaining outside the grooves (step s42).

10 During the curing process (step s41), the ink 5 shrinks towards the bottom of the groove 6, as shown in Figure 2e, by an amount that depends on its composition and which may result, for example, in shrinkage to 25 per cent. of its original volume.

For high levels of shrinkage, further processing, for example, deposition
15 of further layers over the substrate, may be difficult. In this case, the cured insulator material 2 is dry etched to reduce its thickness (step s43), as shown in Figure 2f, although the reduction is arranged to maintain the curved top edge 4, which is advantageous for the reasons set out above. Organic insulators will etch in pure oxygen or an oxygen/sulphur hexafluoride (O_2/SF_6)
20 mixture or oxygen/carbon tetrafluoride (O_2/CF_4) mixture. The thickness is reduced to the extent necessary to be compatible with subsequent processing.

From reading the present disclosure, other variations and modifications will be apparent to persons skilled in the art. Such variations and modifications may involve equivalent and other features which are already known in the field
25 of producing conductive layers on substrates.

Referring to Figure 7, as an alternative to defining a groove in an insulator in the production of a substrate for an active matrix LCD, a printing process such as offset lithography is used to print an insulating precursor 10
30 onto the substrate 1 so as to define a confinement groove 3, and the insulating precursor is then cured to produce the insulating material 10. The groove is again filled using a blading technique, as explained above with reference to Figure 6.

Although claims have been formulated in this application to particular combinations of features, it should be understood that the scope of the disclosure of the present invention also includes any novel features or any novel combination of features disclosed herein either explicitly or implicitly or
5 any generalisation thereof, whether or not it relates to the same invention as presently claimed in any claim and whether or not it mitigates any or all of the same technical problems as does the present invention. The applicants hereby give notice that new claims may be formulated to such features and/or combinations of such features during the prosecution of the present application
10 or of any further application derived therefrom.

CLAIMS

1. A method of producing a conductive layer (5) on a substrate (1), comprising the steps of:

5 defining a groove (3) for the conductive layer (5) using a photodefinable insulator material (2); and

filling the groove (3) with a material capable of forming the conductive layer (5).

10 2. A method according to claim 1, wherein the step of defining the groove (3) comprises:

depositing the insulator material (2) onto the substrate (1);

defining a pattern in the insulator material; and

processing the pattern to form the groove (3).

15

3. A method according to claim 1 or 2, comprising filling the groove (3) using a blading technique.

4. A method according to any one of the preceding claims, wherein
20 the material capable of forming the conductive layer (5) comprises a metal precursor.

5. A method according to any one of claims 1 to 3, wherein the material capable of forming the conductive layer (5) comprises a conductive
25 ink.

6. A method according to claim 4 or 5, further comprising curing the material to obtain the conductive layer (5).

30 7. A method according to claim 6, further comprising etching the insulator material to reduce its thickness relative to the thickness of the conductive layer.

8. A method according to claim 6 or 7, comprising depositing one or more further functional layers over the conductive layer.

5 9. A method according to any one of the preceding claims, wherein the conductive layer comprises a row or column line in an active matrix liquid crystal display.

10 10. An active matrix liquid crystal display including a conductive layer made by a method according to any one of the preceding claims.

11. A device comprising a substrate (1) overlaid with a photodefinable insulator material (2), the material having a groove (3) for a conductive layer (5) defined therein.

15 12. A device according to claim 11, further comprising a conductive layer (5) in the groove (3).

13. A device according to claim 11 or 12, comprising an active matrix liquid crystal display.

14. A method of producing a conductive layer (5) on a substrate (1), comprising the steps of:

25 defining a groove (3) for the conductive layer (5); and
blading a material capable of forming the conductive layer (5) into the groove.

15. A method according to claim 14, comprising defining the groove (3) by printing an insulating material onto the substrate.

16. A method according to claim 14, wherein the step of defining the groove (3) includes depositing a material (2) onto the substrate (1) and defining the groove (3) in the material.

5 17. A method according to claim 16, wherein the material (2) comprises a photodefinable material.

18. A method according to any one of claims 14 to 17, wherein the substrate comprises a substrate for use in an active matrix liquid crystal display.
10

19. A method of producing a conductive layer (5) on a substrate for an active matrix liquid crystal display, the method comprising the steps of printing an insulating material (10) onto the substrate (1) such that the printed material defines a groove (3) for the conductive layer and filling the groove with a material capable of forming the conductive layer (5).
15

20. A method of producing a conductive layer on a substrate substantially as hereinbefore described with reference to Figures 2 to 7 of the accompanying drawings.
20

21. A device including a conductive layer in a groove on a substrate substantially as hereinbefore described with reference to Figures 2 to 7 of the accompanying drawings.
25

ABSTRACT**A METHOD OF PRODUCING A CONDUCTIVE LAYER ON A SUBSTRATE**

5

A method of producing a conductive layer (5) on a substrate (1) comprises depositing an insulator such as a photodefinable insulator (2) on the substrate (1), defining a groove (3) for the conductive layer (5) in the insulator material, filling the groove (3) with a precursor material and curing the material
10 to provide the conductive layer.

[Fig. 2f]




Figure 1



Figure 2a




Figure 2b




Figure 2c




Figure 2d




Figure 2e




Figure 2f




Figure 3

5 / 8




Figure 4




Figure 5

From step s5, step s21,
step s37




Figure 6





Figure 7

THIS PAGE BLANK (USPTO)

PUB/IB2004/052105



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.